Ordered nano-structure of a stamped self-organized protein layer on a HOPG surface using a HFB carrier

著者	Iwanaga Atsushi, Asakawa Hitoshi, Fukuma Takeshi, Nakamichi Momoka, Shigematsu Sakurako, Linder Markus B., Haruyama Tetsuya
著者別表示	浅川 雅, 福間 剛士
journal or publication title	Colloids and Surfaces B: Biointerfaces
volume	84
number	2
page range	395-399
year	2011-06-01
URL	http://doi.org/10.24517/00039983

doi: 10.1016/j.colsurfb.2011.01.032

Ordered nano-structure of a stamped self-organized protein layer on a HOPG surface using a HFB carrier

Atsushi Iwanaga¹⁾, Hitoshi Asakawa²⁾, Takeshi Fukuma²⁾, Momoka Nakamichi¹⁾, Sakurako Shigematsu¹⁾, Markus B. Linder³⁾ and Tetsuya Haruyama^{1)*}

¹ *Department of Biological Functions and Engineering, Kyushu Institute of Technology, Kitakyushu Science and Research Park, Kitakyushu, Fukuoka, 808-0196, Japan*

² *Frontier Science Organization, Kanazawa University, Kakuma-machi, Kanazawa 920-1192, Japan*

³ *VTT Technical Research Center of Finland, VTT Biotechnology, FIN-02044 VTT, Finland*

*All correspondences should be addressed;

Tetsuya Haruyama

haruyama@life.kyutech.ac.jp

Abstract

A groundbreaking method for ordered molecular layer preparation on a solid surface employing the drop-stamp method has been developed by us taking advantage of the characteristics of the HFB molecule as a self-organizer/adsorption carrier. It is a smart method which can be used to prepare a self-organized protein layer on a solid surface without unspecific adsorption or defects. In our previous report, we clarified the self-organizing nature of HFB-tagged protein molecules on a surface of a solution droplet. In this report, a protein layer was prepared on a HOPG surface by using the drop-stamp method with a maltose binding protein (MBP)-tagged HFBII molecule. The structure of the stamped protein layer was investigated using Frequency Modulation Atomic Force Microscopy (FM-AFM) in a liquid condition. The FM-AFM images show that the drop-stamp

1 method can prepare an ordered protein layer on a solid surface smartly. The drop-stamp method
2 using a HFB carrier is a practical method which can be used to prepare an ordered protein layer on a
3 solid substrate surface without unspecific adsorption defects.

5 **Keywords:**

6 Self-organized protein layer, molecular interface, Hydrophobin, Drop-stamp

8 **Introduction**

9 Protein molecules, such as enzymes, have prominent functionalities, *i.e.* catalytic activity and
10 molecular recognitions. By taking advantage of functional proteins, researchers have used proteins
11 in the development of many different types of molecular device, such as biosensors[1, 2],
12 protein-chips[3] bio (enzyme) fuel cells[4, 5]. However, there are difficulties in efficiently creating
13 such molecular devices. In most cases, functional protein molecules are immobilized on the surface
14 of a solid substrate (ex. electrodes, semi-conductors, carbon, glass etc) and they provide the
15 substrate's functions. However, such protein molecules originally functioned in a homogeneous
16 condition in solution. In the case of molecular devices, immobilized molecules have to provide
17 functions in heterogeneous form and have to control a physical structure of molecular layer on solid
18 surface, e.g. molecular density and molecular orientation, in order to provide both good stability and
19 good function. Importance of optimized structure in molecular layer on solid has been noticed by

1 some careful researches. In case of immobilized enzyme activity, the apparent catalytic reaction
2 ratio was drastically changed by a changing of immobilized molecular orientations on solid.
3 Actually, immobilized enzyme can provide higher apparent catalytic activity in case of optimized
4 molecular orientation on solid surface[6]. Affinity reaction of antibody is also very much depending
5 on immobilized molecular orientations[7]. Cultured cell adhesion on solid material is also can be
6 controlled with the structure of molecular layer on a solid surface. Cell adherent can be modulated
7 using thermally responsive polymer-grafted layer on a solid substrate[8]. In that case, cell
8 adherent/non-adherent is modulated through a changing by temperature. As described about some
9 example, accurate molecular layer fabrication on a solid is an indispensable way to design
10 functionalities of biomaterials. In the designing of interfacial function, it is important that the
11 protein-solid interface (molecular-solid interface) is an ordered molecular layer on a solid surface in
12 order to achieve an efficient molecular solid interface[9]. However, conventional methods to
13 immobilize molecules on solid are unable to control this aspect of the molecular layer; control is
14 clearly required in the fabrication of an ordered molecular layer on a solid surface. A controllable
15 methodology for molecular layer preparation is strongly demanded by those in the fields of
16 molecular interfaces and other protein molecular applications.

17 The authors previously proposed that the fabrication of a protein molecular layer could be achieved
18 by using the “drop-stamp method”, which is based on the properties of the unique protein molecule
19 hydrophobin[10-14]. Hydrophobin (HFB) is originally from the cell wall of fungi and is a small

1 amphiphilic protein molecule. HFB can form a very stable self-organized mono-layer at the
2 air/liquid interface. Our research has found that the self-organized HFB monolayer at the air/liquid
3 interface of a solution droplet can be transferred onto a solid surface through a stamping of the
4 droplet onto the solid[15]. If the HFB is tagged with functional proteins through a genetic
5 engineering technique, the fusion protein can form a stable self-organized monolayer at the
6 air/liquid interface, in a similar way to that of the HFB molecule alone, as reported in our previous
7 study[16]. This finding indicates that the tagged HFB can act as a molecular carrier to form a
8 self-organized monolayer at the air/liquid interface. In our previous report, a fusion protein
9 molecule of MBP and HFBII was genetically engineered. The HFBII-MBP fusion protein molecules
10 could form a self-organized monolayer at the air/liquid interface, in a similar way to that of HFBII
11 alone.

12 In this study, we investigate a stamped self-organized MBP-HFBII fusion protein layer on a HOPG
13 surface in a solution using custom-built Frequency Modulation Atomic Force Microscope
14 (FM-AFM) [17, 18]. The FM-AFM was developed to image soft surfaces in a liquid condition with
15 a high degree of sensitivity. Nano-structures of a drop-stamped self-organized molecular layer with
16 MBP-HFBII fusion protein and HFBII were investigated on a solid substrate surface. It will give a
17 valuable information when the drop-stamp method is employed to prepare an biomolecular device
18 that needs an accurate ordered protein layer on a solid substrate.

19

1 **Materials and Methods**

2 **Expression and Purification of HFBII and MBP-HFBII**

3 HFBII was expressed in *Escherichia coli* BL21 (DE3), as previously described[16]. HFBII was
4 purified from a soluble extract to obtain a high-purity level by a two-step process using Ni-NTA
5 chromatography (HisTrap HP column, GE Healthcare) and reversed phase chromatography
6 (Resource RPC Column, GE Healthcare). Maltose-binding protein (MBP) and HFBII fusion protein
7 were designed and expressed in *E. coli* TB1, as previously described[16]. High-purity MBP-HFBII
8 was purified from the *E.coli* cell extract by two-step chromatography: MBPTrap HP column (GE
9 Healthcare) and HisTrap HP column (GE Healthcare). Both purification samples were stored at -20
10 °C after desalting by Slide-A-Lyzer (Pierce) and were lyophilized. The molecular weight and purity
11 was determined, as previously described.

12 **Analysis of the molecular properties at the air/liquid interface**

13 The π -A isotherms were measured by using a KSV minitrough LB system (KSV Instruments) with 1
14 mM acetate buffer, pH 5.0, and 20 °C for the subphase. HFBII and MBP-HFBII fusion proteins
15 were solved with 1 mM acetate-HCl buffer (pH=5.0). The protein solutions were spread on the
16 subphase. After stabilization of the surface pressure, the protein molecules were compressed at a
17 rate of 10 mm/min.

18 **Fabrication of molecular layer on a solid surface by drop-stamp process**

19 HFBII and MBP-HFBII fusion proteins were solved with 1 mM acetate-HCl buffer (pH=5.0). A 10

1 μ L droplet containing HFBII and/or MBP-HFBII fusion protein was positioned onto a polystyrene
2 substrate. The droplet was incubated for 90 min in a humid condition to form a self-organized
3 protein layer. Then, the self-organized protein layer was placed into contact with High Orientated
4 Pyrolytic Graphite (HOPG: NT-MDT) in order to transfer it onto the solid substrate. The
5 drop-stamped HOPG substrate was washed by acetate buffer immediately.

6 **AFM imaging of the stamped protein layer**

7 A custom-built liquid-environment FM-AFM with an ultra-low noise cantilever deflection detection
8 system [17, 18] was used for the imaging of the stamped protein layers. A commercially available
9 AFM controller (Asylum Research, Santa Barbara, CA, USA) was used to operate the FM-AFM.
10 Silicon cantilevers (PPP-NCH: Nanosensors) with a spring constant in the range of 20-40 N/m were
11 used in the experiments. FM-AFM imaging was performed in an acetate buffer solution at room
12 temperature. All data were obtained through repetition experiments in each mixture ratio of
13 MBP-HFBII and HFBII. Similar result of molecular layer structure could be observed in the
14 repetition experiments.

15

16 **Results and Discussion**

17 HFBII is a unique amphiphilic protein molecule. It is a small protein molecule but has a planar
18 hydrophobic domain in about 4 nm^2 of its surface[19]. The HFBII molecule also has self-organizing
19 functionality at the air/liquid interface. HFBII molecules automatically self-organize into a

1 mono-layer membrane at the air/liquid interface. By taking advantage of the unique properties of
2 HFBII, we employed HFBII as a molecular carrier to form an ordered molecular layer on a solid
3 surface. Figure 1 shows the molecular design of HFBII and the genetically engineered HFBII-MBP
4 fusion molecule. The size dimensions of HFBII and MBP are about 2.5 nm and 6 nm, respectively,
5 as shown in Figure 1. The HFBII molecule was tagged to an MBP molecule through a
6 10-amino-acid linker (sequence; NNNNNNNNNN). The linker length is approx. 3nm. Therefore, it
7 would appear that the MBP molecule exhibits fluctuation on HFBII molecular membrane. The
8 fabrication of intermixed system is a tactic technique to perform controlled density of MBP-HFBII
9 fused protein on a solid surface. In the system, density of tagged MBP on self-organized HFB layer
10 can be changed through just change the mixed ratio of MBP-HFBII fused protein and HFBII protein.
11 The π -A isotherms were analyzed to investigate the organized formation of the protein membrane at
12 the air/liquid interface in various mixture ratio of MBP-HFBII protein and HFBII protein (Figure 2).
13 As shown in the result, the surface pressure sharply increased in the case of HFBII molecules at the
14 pure water surface. The high ratio of surface pressure increment suggested that HFBII
15 self-organized on the solution surface smoothly and tightly. The π -A indicated that the occupation
16 area of HFBII was 4 nm^2 . On the other hand, surface pressure increased gradually in the case of
17 HFBII-MBP fusion molecules. The fusion molecules may have a larger occupation area of 30 nm^2 ,
18 which was calculated from the result of the π -A isotherm. This suggested that self-organization of
19 the HFBII-MBP molecule was probably inhibited through steric hindrances caused by the tagged

1 MBP (MW=55700) molecule because it is much bigger than the fused HFB molecule (MW=9300).
2 Such molecular steric hindrance obstructs formation of a self-organized membrane on a solution
3 surface. In order to avoid such obstructions, we developed a groundbreaking tactic. It is a very
4 efficient tactic that employs HFBII molecules in the HFBII-MBP fusion molecule at the air/water
5 interface of the solution droplet when the self-organized membrane is prepared[16]. HFBII plays a
6 role in reducing the obstructions caused by the tagged bulky MBP molecule. In this study, in order
7 to prepare an ordered molecular layer of HFBII-MBP fusion molecules on a HOPG surface with
8 control of its density, HFBII molecules were intermixed with HFBII-MBP fusion molecules at a
9 molar ratio of 4:1, 9:1 and 15:1. In the case of 4:1, 9:1 and 15:1 mixing ratios, the π - A isotherm
10 shows that the slope of increment of surface pressure is sharper than that of the only-MBP fusion
11 protein. This result suggests that these membranes of self-organized proteins consisted of mixed
12 proteins (HFBII and HFBII-MBP) in the ratio of 4:1, 9:1 and 15:1, respectively. The data from our
13 previous report showed, that the mixed HFBII and HFBII-MBP system forms a more stable
14 self-organized membrane at the air/liquid interface, especially in the case of mixing ratios at 4:1 and
15 9:1. This suggests that the HFBII molecule mitigated steric hindrance between the tagged MBP
16 molecules and acts as an alleviator in the cases where there is an appropriate mixing ratio. The
17 membrane of the self-organized protein molecules is formed on the surface of a droplet with a
18 HFBII protein, and it can be transferred to a solid surface by just stamping it onto the substrate[16].
19 As we described in our previous report, we were able to modulate the number of MBP molecules in

1 a HFBII self-organized membrane at air/liquid surface by changing the mixing ratio of HFBII and
2 HFBII-MBP. This finding indicated that the number of MBP molecules on a stamped layer can be
3 controlled both easily and accurately. A self-organized membrane with HFBII and HFBII-MBP
4 fusion molecules (in a mixing ratio of 4:1, 9:1 and 15:1 respectively) were stamped on a HOPG
5 substrate and their structures were investigated using FM-AFM in a liquid condition. The
6 self-organized membrane of HFBII molecules stamped on the HOPG was observed to be uniform
7 (Figure 3a). This result corresponded with the data that showed that HFBII was adsorptive when
8 immobilized as a mono-layer in a stable condition[20]. In the intermixed system, bright points
9 increased on the AFM images when the ratio of MBP-HFBII/HFBII was increased (Figure 3b-d;
10 height of the bright spot was 3-6 nm. Diameter was 5 nm). These results indicated that the MBP
11 molecule was tagged onto the HFBII molecules which formed a self-organized molecular
12 membrane. Basically, the density of the MBP molecule can be controlled by changing the mixing
13 ratio between HFBII and MBP-HFBII. The structure of the stamped protein layer of HFBII on a
14 HOPG substrate is an important factor in the scaffold being able to fabricate a functional protein
15 layer on it successfully. In order to demonstrate the scaffold structure, the stamped HFBII
16 self-organized layer was investigated by FM-AFM in solution. The results showed that the
17 drop-stamped HFBII layer maintained a self-organized ordered structure similar to that at the
18 air/liquid interface (Figure 4a). The HFBII molecules were 2-5 nm in size. This result indicated that
19 the self-organized layer of HFBII was not a crystallized structure, but that these molecules on a

1 HOPG surface were packed at certain intervals of operating molecular interaction. This image is
2 similar to that in the previous report by another group that was observed on dry surface (not
3 stamped on a solid substrate) [19]. In Figure 4b, the arrows show that the molecular layer is
4 consisted of a structure of 2 nm molecules. The molecular size dimension corresponded to that of
5 the HFBII molecule. There is a black part can be observed in the image. We are considering that the
6 black point is a partly-penetrated hole based on z axis profile. As the current procedure of the
7 drop-stamp method has been done manually, stamped solution droplet may stir on the HOPG when
8 the solution droplet was stamped. The mechanical distortion causes some defects. However, most
9 part of the stamped HFBII and HFBII fusion molecules formed ordered structure as seen in other
10 view of AFM images. The structure of the MBP molecule on the HOPG substrate is an important
11 factor to take into account when fabricating a functional protein layer on a solid surface. Our AFM
12 investigations found that, the stamped self-organized fusion protein layer was well ordered due to
13 the use of our mixed drop-stamp technique (HFBII/MBP-HFBII fusion=9:1). The stamped fusion
14 protein layer was analyzed by FM-AFM in solution. White bright points were suspended (Figure
15 5a). These islands of white bright points are consistent with particles of about 5 nm (Figure 5b). The
16 observed size dimension clearly corresponded to that of the MBP molecule (Figure 5c). However, in
17 some parts of the HOPG, there are conditions where the MBP is directly adsorptive on a substrate
18 directly and onto HFBII molecular layer (Figure 5d). Most of the MBP molecule in the 9:1 mixing
19 ratio was measured as having a height between 3 and 6 nm. These results suggest that most of the

1 MBP molecules exhibit fluctuation caused by the 10-amino-acid linker connecting HFBII onto the
2 HOPG substrate.

3

4 **Conclusion**

5 The MBP molecule tagged HFBII is adsorptive when it is stamped on a solid surface. The
6 molecules are successfully self-organized as a monolayer membrane on a solution droplet surface.

7 MBP was tagged to the self-organized HFBII layer on a solid. In the case, MBP and HFBII were
8 linked through 10 amino acid peptide (sequence; NNNNNNNNNN) that provided hint of flexible
9 structure. Then the MBP may fluctuate in solution. It is a very applicable process which can
10 facilitate the design of efficient, functional molecular interfaces for molecular devices.

11

12 **Acknowledgement**

13 Part of this work was supported by the Japan Science and Technology Agency (JST) as part of the
14 R&D project for the Strategic Japanese-Finland Cooperative Program on Functional Materials.

15

16 **References**

- 17 [1] T. Haruyama, Cellular biosensing: Chemical and genetic approaches, *Analytica Chimica Acta*
18 568 (2006) 211-216.
- 19 [2] K.R. Rogers, Recent advances in biosensor techniques for environmental monitoring, *Analytica*
20 *Chimica Acta* 568 (2006) 222-231.
- 21 [3] H. Zhu, M. Snyder, Protein chip technology, *Current Opinion in Chemical Biology* 7 (2003)
22 55-63.

1 [4] R.A. Bullen, T.C. Arnot, J.B. Lakeman, F.C. Walsh, Biofuel cells and their development,
2 Biosensors & Bioelectronics 21 (2006) 2015-2045.

3 [5] F. Davis, S.P.J. Higson, Biofuel cells - Recent advances and applications, Biosensors &
4 Bioelectronics 22 (2007) 1224-1235.

5 [6] T. Cha, A. Guo, X.Y. Zhu, Enzymatic activity on a chip: The critical role of protein orientation,
6 Proteomics 5 (2005) 416-419.

7 [7] P. Peluso, D.S. Wilson, D. Do, H. Tran, M. Venkatasubbaiah, D. Quincy, B. Heidecker, K.
8 Poindexter, N. Tolani, M. Phelan, K. Witte, L.S. Jung, P. Wagner, S. Nock, Optimizing antibody
9 immobilization strategies for the construction of protein microarrays, Analytical Biochemistry 312
10 (2003) 113-124.

11 [8] M. Yamato, C. Konno, M. Utsumi, A. Kikuchi, T. Okano, Thermally responsive polymer-grafted
12 surfaces facilitate patterned cell seeding and co-culture, Biomaterials 23 (2002) 561-567.

13 [9] Z.O. Araci, A.F. Runge, W.J. Do Herty, S.S. Saavedra, Correlating molecular orientation
14 distributions and electrochemical kinetics in subpopulations of an immobilized protein film, Journal of
15 the American Chemical Society 130 (2008) 1572-+.

16 [10] J.M. Kallio, M.B. Linder, J. Rouvinen, Crystal structures of hydrophobin HFBII in the presence
17 of detergent implicate the formation of fibrils and monolayer films, Journal of Biological Chemistry 282
18 (2007) 28733-28739.

19 [11] G.R. Szilvay, T. Nakari-Setälä, M.B. Linder, Behavior of *Trichoderma reesei* hydrophobins in
20 solution: Interactions, dynamics, and multimer formation, Biochemistry 45 (2006) 8590-8598.

21 [12] G.R. Szilvay, A. Paananen, K. Laurikainen, E. Vuorimaa, H. Lemmetyinen, J. Peltonen, M.B.
22 Linder, Self-assembled hydrophobin protein films at the air-water interface: Structural analysis and
23 molecular engineering, Biochemistry 46 (2007) 2345-2354.

24 [13] H.A.B. Wosten, Hydrophobins: Multipurpose proteins, Annual Review of Microbiology 55 (2001)
25 625-646.

26 [14] A. Paananen, E. Vuorimaa, M. Torkkeli, M. Penttilä, M. Kauranen, O. Ikkala, H. Lemmetyinen,
27 R. Serimaa, M.B. Linder, Structural hierarchy in molecular films of two class II hydrophobins,
28 Biochemistry 42 (2003) 5253-5258.

29 [15] S. Ikeno, G.R. Szilvay, M. Linder, H. Aritomi, M. Ajimi, T. Haruyama, Protein dot stamp using
30 hydrophobin as immobilization carrier, Sensors and Materials 16 (2004) 413-420.

31 [16] H. Asakawa, S. Tahara, M. Nakamichi, K. Takehara, S. Ikeno, M.B. Linder, T. Haruyama, The
32 Amphiphilic Protein HFBII as a Genetically Taggable Molecular Carrier for the Formation of a
33 Self-Organized Functional Protein Layer on a Solid Surface, Langmuir 25 (2009) 8841-8844.

34 [17] T. Fukuma, M. Kimura, K. Kobayashi, K. Matsushige, H. Yamada, Development of low noise
35 cantilever deflection sensor for multienvironment frequency-modulation atomic force microscopy, Review
36 of Scientific Instruments 76 (2005) 053704.

37 [18] T. Fukuma, S.P. Jarvis, Development of liquid-environment frequency modulation atomic force
38 microscope with low noise deflection sensor for cantilevers of various dimensions, Review of Scientific

1 Instruments 77 (2006) -043701.
2 [19] J. Hakanpaa, A. Paananen, S. Askolin, T. Nakari-Setälä, T. Parkkinen, M. Penttilä, M.B.
3 Linder, J. Rouvinen, Atomic resolution structure of the HFBII hydrophobin, a self-assembling
4 amphiphile, Journal of Biological Chemistry 279 (2004) 534-539.
5 [20] M. Linder, G.R. Szilvay, T. Nakari-Setälä, H. Soderlund, M. Penttilä, Surface adhesion of fusion
6 proteins containing the hydrophobins HFBI and HFBII from *Trichoderma reesei*, Protein Science 11
7 (2002) 2257-2266.

10 Figure captions

11 Figure 1: Predicted schematic illustration of MBP-HFBII fusion molecule [PDB ID 2B97 and 1N3X]
12 Figure 2: Surface pressure-area (π - A) isotherms of HFBII (●), MBP-HFBII fusion protein (◆), HFBII:MBP-HFBII=4:1 (▼),
13 HFBII:MBP-HFBII=9:1 (■) and HFBII:MBP-HFBII=15:1 (▲)
14 Figure 3: FM-AFM images of HFBII and HFBII intermixed with MBP-HFBII on HOPG in acetate buffer solution (400×400 nm²).
15 Height range of all images is standardized for analysis of difference from solid substrate (black to white: 10 nm). (a) HFBII, $A=0.136$
16 nm, $\Delta f=+20$ Hz, scan speed: 300nm/s. (b) HFBII:MBP-HFBII=15:1, $A=0.136$ nm, $\Delta f=+79$ Hz, scan speed: 976 nm/s. (c)
17 HFBII:MBP-HFBII=9:1, $A=0.136$ nm, $\Delta f=+68$ Hz, scan speed: 1μm/s. (d) HFBII:MBP-HFBII=4:1, $A=0.23$ nm, $\Delta f=-70$ Hz, scan
18 speed: 975 nm/s.
19 Figure 4: FM-AFM images of HFBII on HOPG in acetate buffer solution (a) 100×100 nm², $A=0.271$ nm, $\Delta f=+67$ Hz, scan speed: 500
20 nm/s, height range (black to white): 2.5 nm. (b) 30×30 nm², $A=0.271$ nm, $\Delta f=+76$ Hz, scan speed: 293 nm/s, height range (black to
21 white): 1.2 nm.
22 Figure 5: FM-AFM images of HFBII intermixed with MBP-HFBII (9:1) on HOPG in acetate buffer solution. (a) 250×250 nm²,
23 $A=0.136$ nm, $\Delta f=+66$ Hz, scan speed: 1.25 μm/s, height range (black to white): 6 nm. (b) 100×100 nm², $A=0.136$ nm, $\Delta f=+65$ Hz,
24 scan speed: 500 nm/s, height range (black to white): 6 nm. (c) Profile measured along the lines A-B in (a). (d) Schematic illustration

1 of molecular interface on HOPG substrate.

2

Figure 1

Figure 2

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15

Figure 3

Figure 4

Figure 5